



support.help@bennypass.com
www.bennypass.com

Compound # BC-1001 90 Durometer, Black, Commercial Grade Buna-N Technical Datasheet

Common Names:

NBR (acrylonitrile butadiene rubber), **Buna-N**, **Nitrile**.

General Description:

Most commonly used general purpose o-ring material because of relative low cost, good mechanical properties, and basic resistance to many common lubricants. Specific physical and chemical resistances vary by compound formulation. BC-1001 is formulated to provide value with balance cost and performance. Please contact support.help@bennypass.com for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

Features:

- Relative low cost.
- Good/Excellent resistance to compression set and tear/abrasion.
- Good/Excellent resistance to many petroleum oils/greases, hydraulic fluids, alcohol, ambient water, silicone greases, Di-ester base lubricants and ethylene-glycol based fluids.

Limitations:

- Ozone, direct sunlight, UV, weathering, aromatic fuels, glycol-based brake fluids, polar solvents, non-flammable hydraulic fluids (HFD), aromatic/chlorinated hydrocarbons, ketones, esters, and aldehydes, 15 year shelf life.

Cure System:

Sulphur

(Peroxide cured CPDs available with improved physical, chemical, and thermal properties)

Service Temperature:

-30 to 250°F

(Additional CPDs available with -65°F and +275°F service temps)

Specification:

ASTM 2000 M7BG910 A14 B14 EA14 EO14 EO34

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A	90 +/- 5	88
Color	Black	Black
Tensile Strength, MPa (psi)	10.1 (1,450) min.	13.2 (1,900)

Information within is believed to be accurate and reliable. However, bennypass makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.



support.help@bennypass.com
www.bennypass.com

Ultimate Elongation, %	100 min.	135
------------------------	----------	-----

HEAT RESISTANCE – A14, ASTM D 573 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	+/- 15	+3
Tensile Strength Change, %	+/- 30	+6
Ultimate Elongation Change, %	-50 max.	-25

COMPRESSION SET – B14, ASTM D 395 Method B (22 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set %	25 max.	10

FLUID RESISTANCE, WATER – EA14, ASTM D 471 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	+/- 10	-5
Volume Change, %	+/- 15	+6

FLUID RESISTANCE – ASTM #1 Oil – EO14, ASTM D 471 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	+/- 5	+4
Tensile Strength Change, %	-25 max.	+4
Ultimate Elongation Change, %	-45 max.	-22
Volume Change, %	-10 to +5	-4

FLUID RESISTANCE – IRM 903 Oil, -EO34, ASTM D 471 (70 hrs. @ 100°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points	-10 to +5	-8
Tensile Strength Change, %	-45 max.	-14
Ultimate Elongation Change, %	-45 max.	-19
Volume Change, %	0 to +25	+9

LOW TEMPERATURE RESISTANCE – F17, ASTM D 2137 Method A, 9.3.2	ASTM D2000 Requirements	Typical Test Results
(Non-brittle after 3 min. @ -40°C)	Pass	Pass

Date: 2016-5-9

Information within is believed to be accurate and reliable. However, bennypass makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.