



support.help@bennypass.com
www.bennypass.com

Compound # PB-1000

70 Durometer, Yellow-Translucent, High Performance Polyurethane

Technical Datasheet

Common Names:

Polyurethane (AU, EU)

General description:

Polyurethane is a widely used compound due to its superior strength, tear and abrasion resistance. Polyurethane also provides excellent permeation resistance. Compound PB-1000 uses a specialty Cast TODI cure system which yields greatly increased performance over Millable Gum type Polyurethane materials. Please contact support.help@bennypass.com for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

Features:

- Good hydraulic oil and gasoline resistance
- Resistant to pure aliphatic hydrocarbons (propane, butane, fuel)
- Resistance to mineral and silicone oils and greases
- Resistant to Water, oxygen, ozone and aging
- Excellent tear and abrasion resistance

Limitations:

- Not compatible with acids, ketones, esters, ethers, alcohols, glycols
- Hot water, steam, alkalis and amines

Cure System

Cast TODI Performance Cure

Service Temperature:

-65 to 250° F

PHYSICAL PROPERTY STANDARDS

ORIGINAL PROPERTIES	Specification Requirements	Typical Test Results
Hardness, Shore A	70 +/- 5	73
Color	Translucent	Translucent
Tensile Strength, psi	5,000 min.	5,950
Ultimate Elongation, %	450 min.	660
Modulus @ 100%, psi	-----	850
Modulus @ 300%, psi	-----	990

Information within is believed to be accurate and reliable. However, bennypass makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.



HEAT RESISTANCE – ASTM D 573 (70 hrs. @ 100°C)	Specification Requirements	Typical Test Results
Hardness Change, points	+15 max.	-1
Tensile Strength Change, %	-20 max.	-6
Ultimate Elongation Change, %	-40 max.	-5

COMPRESSION SET – ASTM D 395 Method B (70 hrs. @ 70°C)	Specification Requirements	Typical Test Results
Permanent Set, %	35 max.	18

COMPRESSION SET – ASTM D 395 Method B (70 hrs. @ 100°C)	Specification Requirements	Typical Test Results
Permanent Set, %	65 max.	58

FLUID RESISTANCE - Water – ASTM D 471 (70 hrs. @ 100°C)	Specification Requirements	Typical Test Results
Hardness Change, points	+/- 10	-7
Volume Change, %	-50 max.	-30
Ultimate Elongation Change, %	-50 max.	-1
Volume Change, %	0 to +25	+10

FUEL RESISTANCE – Unleaded Gasoline – ASTM D 471(70 hrs. @ 23°C)	Specification Requirements	Typical Test Results
Hardness Change, points	+/- 10	-7
Tensile Strength Change, %	-60 max.	-30
Ultimate Elongation Change, %	-60 max.	-1
Volume Change, %	0 to +40	+10

OIL RESISTANCE –ASTM # 1 Oil – ASTM D 471 (70 hrs. @ 100°C)	Specification Requirements	Typical Test Results
Hardness Change, points	-5 to +15	-4
Tensile Strength Change, %	-25 max.	+16
Ultimate Elongation Change, %	-45 max.	-8
Volume Change, %	-10 to +5	-1

OIL RESISTANCE – IRM # 903 Oil, - ASTM D 471 (70 hrs. @ 100°C)	Specification Requirements	Typical Test Results
Hardness Change, points	0 to -15	-5
Tensile Strength Change, %	-45 max.	-17
Ultimate Elongation Change, %	-45 max.	-8
Volume Change, %	0 to +35	+5

TEAR RESISTANCE – ASTM D624, Die C	Specification Requirements	Typical Test Results
PLI	400	580

Date: 2016-7-1

Information within is believed to be accurate and reliable. However, bennypass makes no warranty, expressed or implied, that parts supplied in this material will perform satisfactorily in specific applications. It's the customer's responsibility to evaluate prior to use.